

## TEST REPORT

Number : HGHT07436292

Applicant : TONGXIANG FIRST LINE SILK VELVET CO.,LTD  
NO. 80 FUYE ROAD FENGMING ECONOMIC  
DEVELOPMENT ZONE,TONGXIANG  
CITY,ZHEJIANG PROVINCE  
Attn : CHLOE

Date : Oct 13, 2022

### Sample Description As Declared :


No. Of Sample : One (1)  
Fibre Content : -  
Material : Woven Fabric  
Finishing : -  
End Uses : -  
Colour : Camel  
Style No. : -  
Order No./PO No. : FL-W-1-125  
Buyer's Name : -  
Manufacturer's Name : -  
Ref. : -

### Applicant's Provided Care Instruction/Label :

-

Date Sample Received : Oct 09, 2022  
Date Testing Started : Oct 09, 2022

Prepared And Checked By:  
For Intertek Testing Services Ltd.,Hangzhou



Vivian Zhao  
Manager



### Intertek Testing Services Ltd., Shanghai, Hangzhou Branch

2-4,6F, of Block 6, No. 1180, Bin'an Road, High&New Tech Zone (Binjiang), Hangzhou 310052, China

上海天祥质量技术服务有限公司杭州分公司

中国杭州高新区(滨江)滨安路 1180 号 6 号楼 2-4,6 层 邮编:310052

Tel: +86 571 8768 8218 Fax: +86 571 8679 0296

E-mail: hztmr@intertek.com

Attention is drawn to the terms and conditions on Website:

[www.intertek.com.cn/responsibility](http://www.intertek.com.cn/responsibility)

TEST REPORT

Number : HGHT07436292

Tests Conducted (As Requested By The Applicant)

1 Degree Of Weft Bow And Skew (ASTM D3882-08(2020)):

	<u>As Received</u>
Bow Measurement (cm)	1.2 cm
Fabric Width (cm)	146.3 cm
Bowness Percentage (%)	0.8%
Type Of Bow	Bow
	<u>As Received</u>
Skew Measurement (cm)	1.1 cm
Fabric Width (cm)	146.1 cm
Skew Percentage (%)	0.8%
Skew Direction	Z

Remark : The Direction Of Skewness Was Measured From The Left Selvedge With The Face Of The Fabric Being Viewed.

---

End of Report

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*

*This report shall not be reproduced except in full, without written approval of the laboratory.*